

## **AMENDMENTS TO THE CLAIMS:**

This listing of claims will replace all prior versions and listings of claims in the application:

1. (Currently amended) Glass cloth which is composed of warp yarns and weft yarns of the same kind of glass yarn, said glass cloth being obtained by a flattening process under a tension exerted on the glass cloth of not more than 49N/m per 1 m width of the glass cloth, wherein a thickness of the glass cloth is not less than 10  $\mu\text{m}$  and not more than ~~[[50]]~~30  $\mu\text{m}$ , a ratio of warp yarn width to weft yarn width is not less than 0.80 and not more than 1.20~~[[,]]~~ and a ratio of an elongation rate in a length direction when a load in a range of 25 N to 100 N per 25 mm width of the glass cloth is added in a warp yarn direction, to an elongation rate in a width direction when said load is added in a weft yarn direction is not less than 0.80 and not more than 1.20.
- 2-3. (Cancelled).
4. (Currently amended) Glass cloth according to claim 1 ~~[[or 3]]~~, wherein an average diameter of filaments of the glass yarn forming the glass cloth is not less than 3.0  $\mu\text{m}$  and less than 6.0  $\mu\text{m}$  and the number of the filaments of the glass yarn is not less than 50 and not more than 204.
5. (Currently amended) A film substrate composed of one sheet of glass cloth according to claim 1 or ~~[[3]]~~4 and a matrix resin.
6. (Cancelled).